

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 291 090 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:

**14.12.2005 Bulletin 2005/50**

(51) Int Cl.7: **B05D 5/06**

(86) International application number:  
**PCT/JP2001/004178**

(21) Application number: **01932142.1**

(87) International publication number:  
**WO 2001/087502 (22.11.2001 Gazette 2001/47)**

(22) Date of filing: **18.05.2001**

**(54) METHOD FOR FORMING MULTI-LAYER COATING FILM**

**VERFAHREN ZUR HERSTELLUNG EINES VIELSCHICHTIGEN BESCHICHTUNGSFILMS**

**PROCEDE DE FORMATION D'UNE PELLICULE DE PROTECTION A COUCHES MULTIPLES**

(84) Designated Contracting States:  
**DE FR GB**

(30) Priority: **18.05.2000 JP 2000146096**

(43) Date of publication of application:  
**12.03.2003 Bulletin 2003/11**

(73) Proprietors:  
• **KANSAI PAINT CO., LTD.**  
**Amagasaki-shi, Hyogo-ken 661-8555 (JP)**  
• **Toyota Jidosha Kabushiki Kaisha**  
**Toyota-shi, Aichi 471-8571 (JP)**

(72) Inventors:  
• **KOBAYASHI, Yoshiko**  
**Aichi 471-8571 (JP)**

• **UMEMURA, Susumu**  
**Aichi 471-8571 (JP)**  
• **SHIMIZU, Kenta Kansai Paint Co., LTD.**  
**Nishikamo-gun Aichi 470-0206 (JP)**  
• **NAKAO, Yasushi Kansai Paint Co., LTD.**  
**Nishikamo-gun Aichi 470-0206 (JP)**  
• **NAKAMURA, Shigeru Kansai Paint Co., LTD.**  
**Nishikamo-gun Aichi 470-0206 (JP)**

(74) Representative: **Albrecht, Thomas et al**  
**Kraus & Weisert,**  
**Thomas-Wimmer-Ring 15**  
**80539 München (DE)**

(56) References cited:  
**EP-A- 0 379 746 EP-A- 0 507 634**  
**JP-A- 11 147 069 JP-A- 52 043 817**  
**JP-A- 55 056 165 US-A- 4 450 200**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 1 291 090 B1**

**Description****Technical Field**

5 [0001] This invention relates to a process for forming a multi-layer coating film which comprises an intermediate coating film, a metallic coating film and a clear coating film, and which has chipping-resistance and smoothness improved.

**Background Art**

10

[0002] It has already been known to form, on exterior surfaces of automobile body etc., a multi-layer coating film by 3C1B method, i.e., by applying intermediate paint, metallic paint and clear paint in this order, and curing the resultant coatings simultaneously by heating. It is often seen that this multi-layer coating film is hit by gravels spattered by a running car, and thus partially peels off (which phenomenon is called "chipping"). In order to resolve this chipping, it

15

has been proposed to place flexible coating film between coating film layers. This method is, however, undesirable since it increases the number of coating process steps.

[0003] The objective of this invention is to improve, without increasing the number of coating process steps, the chipping-resistance of a multi-layer coating film which is formed by 3C1B method with use of intermediate paint, metallic paint and clear paint.

20

**Disclosure of Invention**

[0004] As a result of assiduous study, the inventors of this invention have now found out that the above-mentioned objective is achieved when the intermediate paint contains 0.5 to 5 phr of flat talc powder of a specific size and has a

25

[0005] This invention relates to a process for forming a multi-layer coating film by applying, to a substrate, intermediate paint, metallic paint and clear paint by 3C1B method, which process is characterized in that said intermediate paint contains 0.5 to 5 phr of flat talc powder of a size of 0.5 to 10  $\mu\text{m}$  in longer direction and 0.01 to 1  $\mu\text{m}$  in thickness, and has a total pigment content of 40 to 100 phr.

30

[0006] In the following, the process of this invention for forming a multi-layer coating film is explained in more detail.

**Modes for Carrying Out Invention**

[0007] The characteristic feature of this invention resides in the use of intermediate paint which contains 0.5 to 5 phr of flat talc powder of a size of 0.5 to 10  $\mu\text{m}$  in longer direction and 0.01 to 1  $\mu\text{m}$  in thickness, and which has a total pigment content of 40 to 100 phr. Owing to this characteristic feature, a multi-layer coating film has successfully been improved in both chipping-resistance and smoothness without increase in the number of coating process steps.

35

[0008] Concrete examples of the intermediate paint which is used in this invention may include organic solvent type or aqueous type liquid paint which is obtained by mixing, with organic solvent and/or water, a base resin such as polyester resin, alkyd resin and acrylic resin having a crosslinking functional group such as hydroxyl group; a crosslinking agent such as melamine resin and blocked polyisocyanate compound; and flat talc of a specific size; and other pigments. Said other pigments include coloring pigments and extender pigments other than flat talc. The size (particle diameter) of these other pigments is suitably equivalent to, or less than, the size of the above-mentioned flat talc powder.

40

[0009] In this specification, "phr" is an abbreviation of "part per hundred parts of resin", which means part(s) by weight per 100 parts by weight of resin solid content of paint.

45

[0010] The flat talc powder which is used in this invention is an inorganic extender pigment having hydrous magnesium silicate as a main component. Said powder are flakes of a size of 0.5 to 10  $\mu\text{m}$ , preferably 1 to 5  $\mu\text{m}$ , in longer direction, and 0.01 to 1  $\mu\text{m}$ , preferably 0.1 to 0.5  $\mu\text{m}$ , in thickness. When the size in longer direction of the flat talc powder used is smaller than 0.5  $\mu\text{m}$ , the chipping resistance of coating film decreases, while, when it is larger than 10  $\mu\text{m}$ , the smoothness of coating film decreases, both of which are undesirable. When talc is replaced by a powder of clay, barium sulfate or mica, it becomes impossible to achieve the object of this invention to simultaneously improve the chipping resistance and smoothness of a multi-layer coating film.

50

[0011] The content of flat talc powder in intermediate paint may be in a range of 0.5 to 5 parts by weight per 100 parts by weight of resin solid content of paint (i.e., 0.5 to 5 phr), preferably 1 to 4 parts by weight (1 to 4 phr). When said content is lower than 0.5 part by weight, the chipping resistance of coating film is not improved, while, when it is higher than 5 parts by weight, the smoothness of coating film decreases, both of which are undesirable.

55

[0012] As other pigments to be compounded in intermediate paint together with flat talc powder, any known coloring pigments and extender pigments which are usually used in intermediate paint are usable. As for the content of said

other pigments, the total content of flat talc powder and such other pigments, i.e., "total pigment content", may be 40 to 100 phr, preferably 60 to 97 phr, especially desirably 80 to 95 phr. When said total pigment content in intermediate paint used is lower than 40 phr, the chipping resistance of coating film decreases, while, when it is larger than 100 phr, the multi-layer film becomes mechanically brittle, both of which are undesirable.

[0013] This intermediate paint may be applied on a metal-made or plastic-made substrate for automobile body on which an under coating such as cationic electrodeposition paint has been applied as circumstances may demand. Paint application may be conducted by any known method. The thickness of coating film of this intermediate paint is suitably 15 to 40  $\mu\text{m}$ , in particular 20 to 35  $\mu\text{m}$ , as a cured film.

[0014] Subsequently, while intermediate coating film is kept uncured, this uncured intermediate coating surface is coated with metallic paint.

[0015] Any known metallic paint is usable, examples of which include usual thermosetting metallic paint which is obtained by mixing, with organic solvent and/or water, a base resin such as polyester resin, alkyd resin and acrylic resin having a crosslinking functional group such as hydroxyl group; a crosslinking agent such as melamine resin and blocked polyisocyanate compound; a metallic pigment such as aluminum flake and titanium oxide-coated mica; and, furthermore, a coloring pigment and an extender pigment as circumstances may demand. Metallic paint is applied by a usual method on the above-mentioned uncured coating surface of intermediate paint. The thickness of coating film of this metallic paint is suitably 10 to 40  $\mu\text{m}$ , preferably 15 to 35  $\mu\text{m}$ , as a cured film.

[0016] Subsequently, while the coating film of this metallic paint is kept uncured, clear paint is further applied.

[0017] Any known clear paint which forms colorless or colored transparent coating film is usable, examples of which include usual thermosetting clear paint which is obtained by mixing, with organic solvent, a base resin such as polyester resin, alkyd resin and acrylic resin having a crosslinking functional group such as hydroxyl group; a crosslinking agent such as melamine resin and blocked polyisocyanate compound; and, furthermore, as circumstances may demand, a coloring pigment or an extender pigment which does not substantially interfere with the transparency of coating film. Clear paint is applied by a usual method on the above-mentioned uncured coating surface of metallic paint. The thickness of coating film of this clear paint is generally 20 to 80  $\mu\text{m}$ , preferably 25 to 50  $\mu\text{m}$ , as a cured film.

[0018] When intermediate paint, metallic paint and clear paint are applied in order in this manner to form an uncured three-layer coating film, and when the three layers of coating film are simultaneously cured by heating at a temperature of about 100 to about 180°C, in particular at about 120 to about 160°C, for about 10 to 40 minutes, a multi-layer coating film as an object of this invention is formed.

[0019] According to the afore-mentioned process of this invention, there is formed, without increase in the number of process steps, a multi-layer coating film which is excellent in both chipping resistance and smoothness, by 3C1B method with use of intermediate paint, metallic paint and clear paint, said intermediate paint containing 0.5 to 5 phr of flat talc powder of a size of 0.5 to 10  $\mu\text{m}$  in longer direction and 0.01 to 1  $\mu\text{m}$  in thickness, and having a total pigment content of 40 to 100 phr.

## Examples

[0020] In the following, this invention is explained in more detail by means of Examples and Comparative Examples. Both part and % are on weight basis, and the thickness of coating film is that of cured coating film.

### Example 1

[0021] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of flat talc of a size of 5  $\mu\text{m}$  in longer direction and 0.5  $\mu\text{m}$  in thickness, 80 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was excellent in both chipping resistance and smoothness (sense of gloss).

### Comparative Example 1

[0022] A multi-layer coating film was formed by the same operation as in Example 1 except that flat talc was not compounded in intermediate paint. Thus obtained multi-layer film was equivalent to that of Example 1 in smoothness, but was inferior thereto in chipping resistance.

**Comparative Example 2**

[0023] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of clay (particle size: 0.1 to 2  $\mu\text{m}$ ), 80 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was equivalent to that of Example 1 in smoothness, but was inferior thereto in chipping resistance.

**Comparative Example 3**

[0024] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of barium sulfate (particle size: 0.1 to 2  $\mu\text{m}$ ), 80 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was equivalent to that of Example 1 in smoothness, but was inferior thereto in chipping resistance.

**Comparative Example 4**

[0025] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of flat mica (5  $\mu\text{m}$  in longer direction, and 0.5  $\mu\text{m}$  in thickness), 80 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was inferior to that of Example 1 in both smoothness and chipping resistance.

**Comparative Example 5**

[0026] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of flat talc of a size of 15  $\mu\text{m}$  in longer direction and 0.5  $\mu\text{m}$  in thickness, 80 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was almost equivalent to that of Example 1 in chipping resistance, but was inferior thereto in smoothness.

**Comparative Example 6**

[0027] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of flat talc of a size of 5  $\mu\text{m}$  in longer direction and 0.5  $\mu\text{m}$  in thickness, 30 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was inferior to that of Example 1 in chipping resistance.

## Comparative Example 7

[0028] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 3 phr of flat talc of a size of 5  $\mu\text{m}$  in longer direction and 0.5  $\mu\text{m}$  in thickness, 106 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was inferior to that of Example 1 in smoothness and chipping resistance.

## Comparative Example 8

[0029] A steel plate which had been coated with cationic electrodeposition paint and then heat-cured was coated with polyester resin • melamine resin-type intermediate paint [containing, in an organic solvent, 20 phr of flat talc of a size of 5  $\mu\text{m}$  in longer direction and 0.5  $\mu\text{m}$  in thickness, 75 phr of titanium white (particle size: 0.2  $\mu\text{m}$ ) and 1 phr of carbon black (particle size: 0.1  $\mu\text{m}$ )] to a film thickness of 30  $\mu\text{m}$ . After left still for two minutes at a room temperature, thus coated steel plate was further coated with thermosetting acrylic resin type metallic paint (film thickness: 15  $\mu\text{m}$ ) and thermosetting acrylic resin type clear paint (film thickness: 40  $\mu\text{m}$ ) in order, and, thereafter, thus applied three layers of coating film were heated at 140°C for 30 minutes and were thereby simultaneously cured. Thus obtained multi-layer coating film was almost equivalent to that of Example 1 in chipping resistance, but was inferior thereto in smoothness.

## Coating Film Property Test

[0030] The multi-layer coating films which had been formed in the above-mentioned Example 1 and Comparative Examples 1 to 8 were measured for chipping resistance and coating surface smoothness by the following method. Results are shown in Table below.

## Chipping Resistance:

[0031] There was sprayed about 500 ml of marble having a diameter of 15 to 20 mm on the surface of multi-layer coating film at an incident angle of 45 degrees, at an air-spray pressure of about 4 kg/cm<sup>2</sup> and an ambient temperature of -20°C, by using Q - G - R Gravelometer (trademark of a product manufactured by Q Panel Co.), and, then, the coating surface was visually observed. O means that, whereas intermediate coating film had slightly peeled off, electrodeposition coating film had hardly peeled off.  $\Delta$  means that, intermediate coating film had much peeled off, and that electrodeposition coating film had partially peeled off. X means that almost all intermediate coating film had peeled off, and that electrodeposition coating film had much peeled off.

## Coating Surface Smoothness:

[0032] With use of a specular glossmeter, reflectance was measured when both incident angle and received angle were 20 degrees, and, thus, the degree of smoothness was examined. The higher the reflectance is the better is smoothness.

	Example	Comparative Example							
	1	1	2	3	4	5	6	7	8
Chipping resistance	O	X	X	X	$\Delta$	O	$\Delta$	$\Delta$	O
Coating surface smoothness	85	90	85	85	60	30	90	75	10

## Claims

1. A process for forming a multi-layer coating film by applying, to a substrate, intermediate paint, metallic paint and clear paint by 3C1B method, which process is **characterized in that** said intermediate paint contains 0.5 to 5 phr of flat talc powder of a size of 0.5 to 10  $\mu\text{m}$  in longer direction and 0.01 to 1  $\mu\text{m}$  in thickness, and has a total pigment

content of 40 to 100 parts per hundred parts of resin (phr).

2. A process of claim 1 wherein the flat talc powder is of a size of 1 to 5  $\mu\text{m}$  in longer direction.
- 5 3. A process of claim 1 wherein the flat talc powder is of a size of 0.1 to 0.5  $\mu\text{m}$  in thickness.
4. A process of claim 1 wherein the flat talc powder is contained in an amount of 1 to 4 phr.
5. A process of claim 1 wherein total pigment content is 80 to 95 phr.
- 10 6. A process of claim 1 wherein the substrate is a metal-made or plastic-made substrate for automobile body which has been coated with cationic electrodeposition paint as an under coating.
7. Articles which have been coated by the process of claim 1.

#### Patentansprüche

- 20 1. Verfahren zur Herstellung eines mehrschichtigen Beschichtungsfilms, wobei auf ein Substrat ein Zwischenanstrichmittel, ein metallisches Anstrichmittel und ein klares Anstrichmittel durch das 3C1B-Verfahren aufgetragen werden, wobei das Verfahren **dadurch gekennzeichnet ist, dass** das Zwischenanstrichmittel 0,5 bis 5 phr an flachem Talkpulver mit einer Größe von 0,5 bis 10  $\mu\text{m}$  in längerer Richtung und 0,01 bis 1  $\mu\text{m}$  in der Dicke enthält und einen Gesamtpigmentgehalt von 40 bis 100 Teile pro 100 Teile Harz (parts per hundred parts of resin (phr)) hat.
- 25 2. Verfahren nach Anspruch 1, wobei das flache Talkpulver eine Größe von 1 bis 5  $\mu\text{m}$  in längerer Richtung hat.
3. Verfahren nach Anspruch 1, wobei das flache Talkpulver eine Größe von 0,1 bis 0,5  $\mu\text{m}$  in der Dicke hat.
4. Verfahren nach Anspruch 1, wobei das flache Talkpulver in einer Menge von 1 bis 4 phr enthalten ist.
- 30 5. Verfahren nach Anspruch 1, wobei der Gesamtpigmentgehalt 80 bis 95 phr ist.
6. Verfahren nach Anspruch 1, wobei das Substrat ein aus Metall hergestelltes oder aus Kunststoff hergestelltes Substrat für eine Kraftfahrzeugkarosserie ist, das mit einem kationischen Galvanisieranstrichmittel als Grundierung beschichtet worden ist.
- 35 7. Gegenstände, die durch das Verfahren nach Anspruch 1 beschichtet worden sind.

#### Revendications

- 45 1. Procédé de formation d'un film de revêtement multicouche consistant à appliquer, à un substrat, une peinture intermédiaire, une peinture métallique et une peinture transparente par un procédé 3C1B, lequel procédé est **caractérisé en ce que** ladite peinture intermédiaire contient 0,5 à 5 pcr de poudre de talc plat d'une dimension de 0,5 à 10  $\mu\text{m}$  dans la direction de la longueur et de 0,01 à 1  $\mu\text{m}$  d'épaisseur, et a une teneur totale en pigments de 40 à 100 parties pour cent parties de résines (pcr).
- 50 2. Procédé selon la revendication 1 dans lequel la poudre de talc plat est d'une dimension de 1 à 5  $\mu\text{m}$  dans la direction de la longueur.
3. Procédé selon la revendication 1 dans lequel la poudre de talc plat est d'une dimension de 0,1 à 0,5  $\mu\text{m}$  en épaisseur.
4. Procédé selon la revendication 1 dans lequel la poudre de talc plat est contenue en une quantité de 1 à 4 pcr.
- 55 5. Procédé selon la revendication 1 dans lequel la teneur totale en pigment est de 80 à 95 pcr.
6. Procédé selon la revendication 1 dans lequel le substrat est un substrat fait de plastique ou fait de métal pour une

**EP 1 291 090 B1**

carrosserie d'automobile qui a été revêtu avec une peinture d'électrodéposition cationique comme sous-couche.

7. Articles qui ont été revêtus par le procédé selon la revendication 1.

5

10

15

20

25

30

35

40

45

50

55